# CERTAINTEED® TYPE C DRYWALL PANEL

| Job Name           |  |
|--------------------|--|
|                    |  |
| Contractor         |  |
|                    |  |
| Date               |  |
|                    |  |
| Products Specified |  |

#### PRODUCT DESCRIPTION

CertainTeed Type C Drywall Panel is an interior drywall panel consisting of an enhanced fire-resistant, non-combustible gypsum core enclosed in ivory-coloured face paper and a strong liner back paper. CertainTeed Type C Drywall Panels provide superior fire performance when used in specific fire-rated Type C assemblies. Long edges are slightly tapered, allowing joints to be reinforced and concealed with joint tape and joint compound. CertainTeed Type C Drywall Panel is available in a variety of lengths and widths.

#### **BASIC USES**

CertainTeed Type C Drywall Panel is used for interior walls and ceilings in residential and commercial applications requiring extended fire ratings. It can be used for installations over wood or steel framing. They are typically nailed or screwed to studs spaced 16" (406 mm) or 24" (610 mm) o.c.

#### **ADVANTAGES**

- UL / cUL / ULC fire rated assemblies up to four hours.
- Consistently high quality.
- Uniformly flat, attractive appearance.
- High edge hardness.
- No wavy edges, warps, bows or deformities.
- Uniform high-strength cores eliminate crumbling, cracking.
- Edge tapers consistent to form perfect joints.
- Excellent thermal barrier and sound attenuation qualities.
- GREENGUARD® Gold Certified

# **INSTALLATION**

#### LIMITATIONS

- Exposure to continuous moisture or extreme temperatures should be avoided. Not recommended for continuous exposure to temperatures exceeding 125° F (52° C).
- Framing spacing should not exceed 24" (610 mm) o.c.
- Should be stored indoors and off ground surface.
- Panels should be stacked flat with care taken to prevent sagging or damage to edges, ends and surfaces.
- Storing panel lengthwise leaning against the framing is not recommended.
- Panels should be carried, not dragged, to place of installation to prevent damaging finished edges.
- Cutting and scoring should be done from the face side.
- In cold weather or during joint finishing, temperatures within the enclosure should stay within the range of 50° to 95° F (10° to 35° C) and with sufficient ventilation to carry off excess moisture.
- CertainTeed Type C can be substituted in an equivalent thickness in any fire resistance rated assembly specifying Type X.
- Where CertainTeed Type C is specified to attain a fire resistance rating, CertainTeed Type X of equivalent thickness cannot be substituted.



## **PRODUCT DATA**

| PROPERTIES | TYPE C DRYWALL PANELS   |  |
|------------|---|--|
| Thickness  | 1/2" (12.7 mm), 5/8" (15.9 mm)  |  |
| Width      | 4' (1220 mm)  |  |
| Length     | 1/2" - 12' (3660mm)<br>5/8" - 8', 9', 10', 12'<br>(2440, 2740, 3050, 3660 mm)       |  |
| Weight     | 1/2" (12.7 mm) - 1.9 lb/ft² (9.3 kg/m²)<br>5/8" (15.9 mm) - 2.3 lb/ft² (11.2 kg/m²) |  |
| Edges      | Tapered   |  |
| Packaging  | Two pieces per bundle, face-to-face and end-taped                                   |  |

Custom lengths may be available on special order. Consult your CertainTeed sales representative.

### **TECHNICAL DATA**

| APPLICABLE STANDARDS AND REFERENCE |  |  |  |  |
|------------------------------------|--|--|--|--|
| Product Standard                   | ASTM C1396                                 |  |  |  |
| Installation Guidelines            | ASTM C840 / GA-216                         |  |  |  |
| Finishing Guidelines               | ASTM C840 / GA-214                         |  |  |  |
| Code References                    | International Building Code (IBC)          |  |  |  |
| Code References                    | International Residential Code (IRC)       |  |  |  |
| Code References                    | National Building Code of Canada<br>(NBCC) |  |  |  |
| UL/ULC Designation                 | Туре С                                     |  |  |  |



| PHYSICAL PROPERTIES                               | 1/2" (12.7 mm) TYPE C  | 5/8" (15.9 mm) TYPE C        | TEST METHOD                      |
|---|------------------------|------------------------------|----------------------------------|
| Nominal Width                                     | 4' (1220 mm)           | 4' (1220 mm)                 | -                                |
| Standard Lengths                                  | 12' (3660 mm)          | 8' (2440 mm) - 12' (3660 mm) | -                                |
| Face Surface                                      | Paper                  | Paper                        | -                                |
| Weight - lb/ft² (kg/m²)                           | 1.9 lb/ft² (9.3 kg/m²) | 2.3 lb/ft² (11.2 kg/m²)      | -                                |
| Edge Profile                                      | Tapered                | Tapered                      |                                  |
| Surface Burning Characteristics - Flame Spread    | 15 (0)                 | 15 (0)                       | ASTM E84 / UL 723 (CAN/ULC-S102) |
| Surface Burning Characteristics - Smoke Developed | 0 (0)                  | 0 (0)                        | ASTM E84 / UL 723 (CAN/ULC-S102) |
| Combustibility                                    | Non-Combustible        | Non-Combustible              | ASTM E136                        |
| Nail Pull   | ≥ 77 lbf (343 N)       | ≥ 87 lbf (387 N)             | ASTM C473 (Method B)             |
| Core Hardness - End                               | ≥ 11 lbf (49 N)        | ≥ 11 lbf (49 N)              | ASTM C473 (Method B)             |
| Core Hardness - Edge                              | ≥ 11 lbf (49 N)        | ≥ 11 lbf (49 N)              | ASTM C473 (Method B)             |
| Flexural Strength - Parallel                      | ≥ 36 lbf (160 N)       | ≥ 46 lbf (205 N)             | ASTM C473 (Method B)             |
| Flexural Strength - Perpendicular                 | ≥ 107 lbf (476 N)      | ≥ 147 lbf (654 N)            | ASTM C473 (Method B)             |
| Humidified Deflection                             | ≤ 1-1/4" (32 mm)       | ≤ 5/8" (16 mm)               | ASTM C473                        |

#### **RECOMMENDATIONS**

Installation of CertainTeed® Type C Drywall Panels should be consistent with methods described in the standards and references noted. Cutting should be from the face side of the panels for best results.

#### **DECORATION**

CertainTeed Type C Drywall Panel accepts most types of paints, texture and wall covering materials. The surface shall be primed with a full-bodied latex primer before applying a final decorative material. This will equalize the suction between the joint compounds and the paper surface.

For best painting results, all surfaces, including joint compound, should be clean, dust-free and not glossy. If glossy paints are used, a thin skim coat of compound over the entire surface, Level 5 finish, is recommended to reduce highlighting or joint photographing. This method is also recommended for areas of critical sidelighting of natural or artificial light sources.

A sealer application under wallpaper or other wall covering is also recommended so the panel surface will not be damaged if the covering is subsequently removed during redecorating. Joint treatment must be thoroughly dry before proceeding with primer-sealer application and final decoration.

### **BIM/CAD INFORMATION**

The BIM and CAD UL fire rated assemblies and sound assemblies can be found on CertainTeed's BIM and CAD Design Studio at bimlibrary.saint-gobain.com/certainteed. CertainTeed's BIM and CAD Design Studio provides BIM and CAD details to many UL fire rated assemblies and sound assemblies in easy to view experience. Plus, downloadable Revit and DWG and PDF CAD Details are available.

#### **SUSTAINABILITY**

Sustainable documentation, including recycled content, EPDs, HPDs, VOC Certifications, can be found at saintgobain.ecomedes.com.

#### **NOTICE**

The information in this document is subject to change without notice. CertainTeed assumes no responsibility for any errors that may inadvertently appear in this document.

For Fire Resistance, no warranty is made other than conformance to the standard under which the assembly was tested. Minor discrepancies may exist in the values of ratings, attributable to changes in materials and standards, as well as differences between testing facilities. Assemblies are listed as "combustible" (wood framing) and "noncombustible" (concrete and/or steel construction).





The Health Product Declaration' logo is a trademark or service mark of Health Product Declaration Collaborative, Inc., in the United States and in other countries and is being used herein under license.









